

Dielectric, electro-optical and spectroscopic properties of silver doped zinc oxide-ferroelectric liquid crystal composite system

Kaushlendra Agrahari^{1*}, Sanjeev Kumar Trivedi¹, Ram Raseele Awasthi¹, Vivek Kumar Nautiyal², Rakesh Kumar Sonker³, Rajiv Manohar⁴

¹*Faculty of Engineering and Technology, Khwaja Moinuddin Chisthi Language University, Lucknow, India*

²*Department of Physics, Chaudhary Charan Singh University, Meerut, India*

³*Department of Physics, Acharya Narendra Dev College, University of Delhi, Delhi, India*

⁴*Department of Physics, University of Lucknow, Lucknow, India*

Received: 1 February 2023;

Accepted: 2 April 2023;

<http://dx.doi.org/10.57647/J.JTAP.2023.1702.29>

Oxford OX29 4DA; GB; <https://oiccpres.com>;

Dielectric, electro-optical and spectroscopic properties of silver doped zinc oxide-ferroelectric liquid crystal composite system

Kaushlendra Agrahari^{1*}, Sanjeev Kumar Trivedi¹, Ram Raseele Awasthi¹, Vivek Kumar Nautiyal², Rakesh Kumar Sonker³, Rajiv Manohar⁴

¹Faculty of Engineering and Technology, Khwaja Moinuddin Chisthi Language University, Lucknow-226013

²Department of Physics, Chaudhary Charan Singh University, Meerut-250004

³Department of Physics, Acharya Narendra Dev College, University of Delhi, Delhi-110019

⁴Department of Physics, University of Lucknow, Lucknow-110019

Abstract:

In the present study, silver doped zinc oxide nanoparticles (NPs) have been added in the pristine ferroelectric liquid crystal (FLC). The dielectric, electro-optical and spectroscopic properties was investigated of the pristine FLC and FLC-NPs composite system. The dispersion of NPs into the pristine FLC material sturdily influences the various properties of composite system. Due to dispersion of NPs, a rapid increment in the dielectric permittivity and faster switching was observed for the FLC-NPs composite system. Absorbance of the UV light got diminished in the presence of silver doped zinc oxide NPs. Photoluminescence emission of the pristine FLC material has been quenched after the addition of NPs and a red shift was also detected. The possible applications of this investigation have been suggested in the letter.

Keywords: composite system; dielectric permittivity; absorbance; photoluminescence.

1. Introduction: Liquid Crystals (LCs) are partially ordered, anisotropic fluids, which are thermodynamically located between the crystalline solid and isotropic liquid. They exhibit orientational or low dimensional positional order of their long molecular axis which results into anisotropic physical properties, such as refractive index, dielectric permittivity, elastic constant, or electric conductivity. One of the major applications of LCs is displays and photonic devices. Their operation is based on electro-optical effects in LCs, with which their dielectric and conductive properties are closely coupled [1-3]. Among the LC materials, Ferroelectric LCs (FLCs) have gained intense attention of researchers in recent years due to their remarkable properties i.e. fast switching, low threshold voltage, improved optical contrast, memory effect, wide viewing angle characteristics, etc. [4-6]. FLC materials exhibit the ferroelectric properties due to the low symmetry of chiral smectic C (SmC*) phases [7].

At the same time, ground-breaking developments have been made in the fields of nanotechnology and nanoscience, which led to the birth of a series of novel nanomaterials [8-11]. These nanostructured materials, have achieved remarkable academic and industrial attention due to their size-dependent electronic, optical, magnetic, and chemical properties and have been widely used in almost every field of science from energy, optics, computing, biosciences and medical sciences [12-14]. With the continuous advancement of technology, enrichment in the basic properties of available LCs is exceedingly required. Dispersion of LC compounds with different nanoparticles (NPs) is the most popular approach adopted to improve the physical and electro-optical properties of LC devices. Certainly, when the nanomaterials encounter liquid crystals, a highly interesting and unique synergy will be observed, leading to an abundance of exclusively new and potential applications [15-19]. Various different types of NPs such as organic, semiconducting, ferromagnetic, metallic, and insulating are being used to produce technologically improved electro-optic devices [20-24]. As a dopant for LCs, metal oxide NPs are interesting materials with intriguing properties and have received immense interest in the scientific community owing to their exclusive physical and chemical properties resulting from their limited size and a high density of edge surface sites [25-27]. Singh et al. have found the occurrence of photoluminescence in FLC by doping it with Cu-ZnO NPs [28]. Sharma et al. have reported an increase in the contrast ratio, birefringence and band gap after the dispersion of ZnO NPs in NLCs [29]. Incorporation of Au/SnO₂ Nanocrystals (NCs) enhances the optical tilt angle, PL intensity and reduces saturation voltage of a FLC mixture as observed by Doke et al. [30]. This modification in electrical and optical properties was attributed to change in dynamics of FLC molecules in presence of the NCs. Ayeb et al. have found that doping of pure and copper-incorporated

TiO₂ NPs in NLC 5CB decreases the dielectric anisotropy, response time and splay elastic constant [31].

Zinc oxide (ZnO) is a wide and direct bandgap (about 3.37 eV at room temperature) semiconductor with high exciton binding energy (60 meV at room temperature), and unique optical and luminescence properties [32-34]. Doping in ZnO with selective metals could amend its luminescent characteristics and accelerate the course of their practical applications [35-37]. The diffusion of copper or silver into ZnO can induce variations in its lattice structure and correspondingly, in the interrelated physical properties. Therefore, in this letter, we report the dielectric, electro-optical and spectroscopic properties of pristine FLC and silver doped zinc oxide nanoparticles-FLC composite system.

2. Experimental Details:

The host FLC material used in the present study is Felix 16/100 (Clariant Chemicals Co. Ltd.) and the phase transition of the sample is Cr, SmC*, SmA, N*, and Iso at -20°C, 72°C, 82°C, and 90-94°C. The nanocrystalline powder of Ag-doped ZnO was synthesized by chemical co-precipitation method [38]. For making the composite, first we dissolve the optimized concentration (0.5 wt.%) of NPs into the Chloroform and then take the desired amount of solution to disperse in the host FLC material. After the dispersion, composite was homogenized with an ultrasonic mixer for 5 h at 100 °C temperature. The fabrication of LC cells has already been described in our previous work [24]. The pristine FLC and composite was filled in the assembled cells by capillary method at a temperature higher than the isotropic temperature of the FLC material.

3. Results and discussion:

The frequency dependence of the dielectric permittivity for the pristine FLC and FLC-NPs composite system at room temperature has been shown in figure 1. The addition of silver doped zinc oxide NPs in the pristine FLC causes an increase in the value of dielectric permittivity which is related to the strength of the helical geometry of the FLC molecules. The enhancement in effective dipole moment (increase in net polarization) of the composite system on the addition of NPs increases the dielectric permittivity. Notably NPs prepared by hydrothermal method have more uniform size and possess only some surface defects. The higher interaction of the FLC molecules with surface defects increases the net dielectric permittivity of FLC-NPs composite system.

Fast switching time is one of the basic requirements for display applications and was determined using polarization reversal technique by applying a square wave of appropriate frequency. The voltage dependence of response time (τ) for pristine FLC and FLC-NPs composite system indicates that τ decreases with an increase in voltage as shown in figure 2. It is evident from the figure that the switching time of FLC molecules gets faster in the presence of NPs. The probable reason for the faster switching process is the lower value of rotational viscosity which offers a decreased viscous torque. Therefore, the faster response of composite system is attributed to the reduced viscous torque.

Figure 3 represents the absorbance in arbitrary unit on the wavelength scale (nm) for the pristine FLC and FLC-NPs composite system. The UV-visible absorption study was performed at room temperature to examine the absorbance of white light by the pristine FLC and FLC-NPs composite. It is noted from the graph that pristine FLC and FLC-NPs composite absorb a broad regime of UV light between 310 and 360 nm. The absorbance of the FLC-NPs composite is lower than the pristine FLC and a major absorbance peak was found at 331 nm for the pristine FLC. This absorption peak may be attributed to the π - π^* transitions which are usually observed in all the thermotropic LCs. The perturbation in the geometry of the FLC molecules by the dopant nanoparticles is accountable for the reduction in the absorbance of FLC-NPs composite. Another reason behind the decrease in the absorbance might be due to the scattering centers formed in the presence of NPs.

The variation of photoluminescence (PL) intensity at wavelength scale for the pure FLC and composite system has been depicted in figure 4. The absorbance wavelength was selected as excitation wavelength for the PL measurements. From the figure, it is obvious that the PL intensity of the pristine FLC material has been decreased after the addition of NPs which may be due to absorption of major portion of PL emission of the FLC material by the NPs. Besides the reduction in PL intensity, a slight red shift has also been observed in the PL emission because NPs are acting as PL quencher in the pristine FLC. The PL emission peak was centered at 364 nm and 378 nm for the pristine FLC and FLC-NPs composite system, respectively.

4. Conclusion:

In summary, Ag-doped ZnO nanoparticles were dispersed in the pristine FLC Felix 16/100 and the dielectric, optical and electro-optical properties were investigated for the composite system. Due to the alignment capability of NPs, the optical micrograph of composite system was found to be altered. The relative permittivity of composite system was

found to be increased as the dipole moment of NPs supported the dipole moment of pristine FLC and effective dipole moment was increased. The switching time gets faster for the composite system owing to reduced viscous torque and rotational viscosity. Absorbance and photoluminescence have been found to be decreased for the composite system. The observed outcome of the present study may be applied to faster switching displays and charge storing devices.

References

- [1] D. Demus, J.W. Goodby, G.W. Gray, H.W. Spiess, V. Vill, Wiley-VCH, Weinheim, 1998.
- [2] T. Kato, N. Mizoshita, K. Kishimoto, *Angew. Chem. Int. Ed.* 45 (2005) 38–68.
- [3] J.P.F. Lagerwall, G. Scalia, *Curr. Appl. Phys.* 12 (2012) 1387–1412.
- [4] F. Castles, S.M. Morris, D.J. Gardiner, Q.M. Malik, H.J. Coles, *J. Soc. Inf. Disp.* 18 (2010) 128.
- [5] A. Andreev, T. Andreeva, I. Kompanets, N. Zalyapin, *Appl. Sci.* 8 (2018) 2429.
- [6] Q. Guo, K. Yan, V. Chigrino, H. Zhao, M. Tribelsky, *Cryst.* 9 (2019) 470.
- [7] R.B. Meyer, L. Liebert, L. Strzelecki, P. Keller, *J. Phys. Lett.* 36 (1975) 69–71.
- [8] T. Hegmann, H. Qi, V.M. Marx, *J. Inorg. Organomet. Polym. Mater.* 17 (2007) 483–508.
- [9] A. Mnyusiwalla, A.S. Daar, P.A. Singer, *Nanotech.* 14 (2003) R9.
- [10] C. Burda, X. Chen, R. Narayanan, M.A. El-Sayed, *Chem. Rev.* 105 (2005) 1025–1102.
- [11] J. Liu, H. He, D. Xiao, S. Yin, W. Ji, S. Jiang, D. Luo, B. Wang, Y. Liu, *Mater.* 11 (2018) 1833.
- [12] M.W. Chik, Z. Hussain, M. Zulkefeli, M. Tripathy, S. Kumar, A.B.A. Majeed, K. Byrappa, *Drug Deliv. Transl. Res.* 9 (2018) 578–594.
- [13] O.C. Farokhzad, R. Langer, *ACS Nano*, 3 (2009) 16–20.
- [14] F.S. Kim, G. Ren, S.A. Jenekhe, *Chem. Mater.* 23 (2010) 682–732.
- [15] J.W. Goodby, I.M. Saez, S.J. Cowling, V. Görtz, M. Draper, A.W. Hall, S. Sia, G. Cosquer, S.-E. Lee, E.P. Raynes, *Angew. Chem. Int. Ed.* 47 (2008) 2754–2787.
- [16] H. Qi, T. Hegmann, *J. Mater. Chem.* 18 (2008) 3288–3294.
- [17] C. Blanc, D. Coursault, E. Lacaze, *Liq. Cryst. Rev.* 1 (2013) 83–109.
- [18] U. Shivakumar, J. Mirzaei, X. Feng, A. Sharma, P. Moreira, T. Hegmann, *Liq. Cryst.* 38 (2011) 1495–1514.
- [19] I. Dierking, *Nanomat.* 8 (2018) 453.

- [20] P. Selvaraj, K. Subramani, B. Srinivasan, C.J. Hsu, C.Y. Huang, *Sci. Reports* 10 (2020) 14273.
- [21] K. Agrahari, G. Pathak, R. Katiyar, G. Yadav, T. Vimal, S. Pandey, D.P. Singh, S.K. Gupta, R. Manohar, *Mol. Cryst. Liq. Cryst.* 652 (2017) 195–205.
- [22] T. Vimal, S. Pandey, S.K. Gupta, D.P. Singh, K. Agrahari, G. Pathak, S. Kumar, P.K. Tripathi, R. Manohar, *Liq. Cryst.* 45 (2017) 687–697.
- [23] S.K. Prasad, M.V. Kumar, T. Shilpa, C.V. Yelamaggad, *RSC Adv.* 4 (2014) 4453–4462.
- [24] K. Agrahari, G. Pathak, T. Vimal, K. Kurp, A. Srivastava, R. Manohar, *J. Mol. Liq.* 264 (2018) 510–514.
- [25] H.H. Kung, Elsevier, Amsterdam, 1989.
- [26] V.E. Henrich, P.A. Cox, Cambridge University Press, Cambridge, UK, 1994.
- [27] J.A. Rodriguez, M.F. Garcia, Wiley, New Jersey, 2007.
- [28] D.P. Singh, S.K. Gupta, A. Srivastava, R. Manohar, *J. Lumin.* 139 (2013) 60–63.
- [29] A. Sharma, P. Malik, R. Dhar, P. Kumar, *Bull. Mater. Sci.* 42 (2019) 215.
- [30] S. Doke, P. Ganguly, S. Mahamuni, *Liq. Cryst.* 47 (2020) 2305–2312.
- [31] H. Ayeb, S. Alaya, M. Derbali, L. Samet, J. Bennaceur, F. Jomni, T. Soltani, *Liq. Cryst.* 48 (2021) 223–232.
- [32] I.A. Ezenwa, *Res. J. Chem. Sci.* 2(3) (2012) 26–30.
- [33] Z.L. Wang, *J. Phys. Condens. Matter.* 16 (2004) 829–858.
- [34] M. Suche, S. Christoulakis, K. Moschovis, N. Katsarakis, G. Kiriakidis, *Thin Sol. Films* 515 (2006) 551–554.
- [35] M. Ghosh, A. K. Raychaudhuri, *J. Appl. Phys.* 100 (2006) 034315.
- [36] X.B. Wang, C. Song, K.W. Geng, F. Zeng, F. Pan, *Appl. Surf. Sci.* 253 (2007) 6905.
- [37] B.P. Zhang, N.T. Binh, Y. Segawa, K. Wakatsuki, *Appl. Phys. Lett.* 83 (2003) 1635.
- [38] R. Singh, D.P. Singh, P. Gupta, P. Jain, Sanchita, T. Mishra, A. Kumar, S.S. Dhawan, P.A. Shirke, *Indus. Crops Prod.* 127 (2019) 94–109.




Fig. 1 Variation of dielectric permittivity with frequency for pristine FLC and FLC-NPs composite system.

ACCEPTED




Fig. 2 Variation of response time with applied voltage for pristine FLC and FLC-NPs composite system.

ACCEPTED




Fig. 3 Variation of absorbance with wavelength for pristine FLC and FLC-NPs composite system.

ACCEPTED




Fig. 4 Variation of PL intensity with wavelength for pristine FLC and FLC-NPs composite system.

ACCEPTED