Int. J. Bio-Inorg. Hybr. Nanomater., 6(2): 85-87, Summer 2017

Synthesis SiO₂-TiO₂ nanomposite materials; characterization and photocatalytic activity

M. Golestaneh*

Department of Science, Farhangian University, Tehran, Islamic Republic of Iran

Received: 16 April 2017; Accepted: 31 May 2017

ABSTRACT: SiO_2 -TiO_2 nanomposite materials have been synthesized by Sonochemical method from tetraethylorthotitanate and tetraethylorthosilicate. The synthesized products were characterized by X-ray diffraction (XRD), scanning electron microscopy (SEM), Fourier transform infrared (FT-IR) spectrum, electron dispersive X-ray spectroscopy (EDX) and ultraviolet–visible (UV–Vis). The results revealed that compared to SiO_2 and TiO_2 , SiO2-TiO_2 nanomposite materials display smaller crystal size, greater band gap energy. The photocatalytic activity of the synthesized products has been compared in the photodegradation activity of methylene orange (MO).

Keywords: Methylene orange; Nanomposite; Photocatalytic; Photodegradation; Sonochemical; Water purification

INTRODUCTION

Water purification is one of the most important issues in environmental science and synthetic dyes are the main pollutant groups of wastewater. Even in low quantities, presence of dyes can cause serious environmental problems, for instance, growth of aquatic bacteria can be inhibited by interference of penetration of sunlight into water by organic dye molecules. Therefore, much effort has been made to reduce the concentration of organic dyes in the wastewater. Use of photocatalysts has been considered as one of the most promising ways of removing organic compounds from water.

Recently, a TiO_2/SiO_2 mixed oxide was reported to be more active as a photocatalyst than pure titania. The addition of SiO₂ to TiO₂ enhances the thermal stability of the anatase phase and increases the surface area. Cheng, *et al.*, also reported that silica-doped TiO₂ possessed high photocatalytic activity due to the suppression of the anatase to rutile phase transition and the formation of oxygen vacancies (Gholami, *et al.*, 2013, Kim, *et al.*, 2012, Cheng, *et al.*, 2003).

MATERIALS AND METHODS

All of reagents and solvents were purchased from Merck (proanalysis) and were dried using molecular sieves (Linde 4 Å). XRD patterns were recorded by a Rigaku D-max C III, X-ray diffractometer using Ni-fil-

^(*) Corresponding Author - e-mail: m.golestaneh@cfu.ac.ir




Fig. 1. The corresponding linear portion of the plots of $(\alpha h \vartheta)^{1/2}$ against h ϑ

tered Cu Ka radiation. Scanning electron microscopy (SEM) images were obtained on a Philips XL-30ES-EMequipped with an X-ray energy dispersive detector. Transmission electron microscopy (TEM) images were obtained on a PhilipsEM208 transmission electron microscope with an accelerating voltage of Paper Preparation

RESULTS AND DISCUSSION

The energy gaps of as-prepared product are shown (Fig. 1).

The photocatalytic activity of the SiO_2 -TiO₂ nanomposite materials was evaluated by monitoring the degradation of MO in an aqueous solution, under irra-




Fig. 2. Decolorization of MB dye of \rm{SiO}_2, \rm{TiO}_2 and \rm{SiO}_2/\rm{TiO}_2 nanomposite materials

diation with visible light. Without light or nanostructures, nearly no MO was break down after 200 min, revealing that the contribution of self-degradation was insignificant. However, SiO_2 -TiO₂ nanomposite materials exposed high photocatalytic activity. The heterogeneous photocatalytic processes include many steps, such as diffusion, adsorption and reaction, appropriate distribution of the pore is advantageous to diffusion of reactants and products, which prefer the photocatalytic reaction. In this research, the enhanced photocatalytic activity may be ascribed to suitable distribution of the pore, high hydroxyl content and high separation rate of photo induced charge carriers (Fig. 2).

CONCLUSIONS

 SiO_2/TiO_2 nanomposite with enhanced photocatalytic activity under UV light were prepared by sonochemical method. SiO_2/TiO_2 nanomposite exhibited much higher photocatalytic activity than SiO_2 and TiO_2 under UV light. Such outstanding photocatalytic activity of SiO_2/TiO_2 nanomposite can be attributed to the increased adsorption of organic substrate and the low recombination rate of photogenerated electrons and holes

REFERENCES

- Gholami, T., Salavati-Niasari, M., Bazarganipour, M., Noori, E., (2013). Synthesis and characterization of spherical silica nanoparticles by modified Stöber process assisted by organic ligand. Superlattices and Microstruct., 61: 33-41.
- Kim, C.S., Shin, J.W., An, S.H., Jang, H.D., Kim, T.O., (2012). Photodegradation of volatile organic compounds using zirconium-doped TiO₂/SiO₂ visible light photocatalysts. Chem. Eng. J., 204–206: 40-47.
- Cheng, P. Zheng, M., Jin, Y., Huang , O., Gu, M., (2003). Preparation and characterization of silicadoped titania photocatalyst through sol–gel method. Mater. Lett. 57(20): 2989-2994.

AUTHOR (S) BIOSKETCHES

Mahshid Golestaneh, Assistant professor, Department of Science, Farhangian University, Tehran, Islamic Republic of Iran, *Email: m.golestaneh@cfu.ac.ir*

lp